

Test Report

Number : TWNC00587140

Applicant: Maymom, LLC
No 20-7 Aly 19 LN333
ChungCheng RD Chunan Mioli County Taiwan

Date : Mar 08, 2017

Sample Description:

One (1) group of submitted samples said to be :

Item Name : Breast Pump Parts
Item No. : M017-R, AP002-C, AP002-T
Batch No. : Feb 2017
Quantity : 1 Bag
Agent : Maymom
Manufacturer : Maymom
Buyer : Maymom
Country of Origin : Taiwan
Goods Exported to : USA, UK, CA, China, DE, AU, FR, IT, ES
Date Sample Received : Feb 24, 2017
Date Test Started : Feb 24, 2017

Test Conducted:

As requested by the applicant, for details please refer to attached pages.

Conclusion:

Please see page two.

Authorized by:
On Behalf of Intertek Testing Services
Taiwan Limited



Matt Wang
Sr. Manager



Test Report

Number : TWNC00587140

Conclusion:

<u>Tested Samples</u>	<u>Standard</u>	<u>Result</u>
Submitted Samples	As per applicant's provided requirement	
	– Overall Migration Test	Pass
	– Specific Migration Of Bisphenol A (BPA) Test	Pass

Note: The migration tests were conducted once according to the applicant's request.

Test Condition:

Test Item	Overall Migration Test
Condition	60°C for 12 Hours
Food Simulant	50% Ethanol

Test Condition:

Test Item	Specific Migration Test
Condition	60°C for 12 Hours
Food Simulant	50% Ethanol

Authorized by:
On Behalf of Intertek Testing Services
Taiwan Limited



Matt Wang
Sr. Manager





Number : TWNC00587140

Test Conducted :

1. Overall Migration Test For Plastic Food Contacting Materials/Articles

With Reference to Commission Regulation (EU) No. 10/2011 and the migration test was conducted once.

I. Test Condition:
60°C for 12 Hours

II. Test Results :

<u>Food Simulant</u>	<u>Result (mg/dm²)</u>	<u>Limit # (mg/dm²)</u>
	<u>Light purple plastic (the biggest)</u>	
50% (v/v) Ethanol	<1	10

Remarks: < = Less than
= As per applicant's provided requirement
Solvents & test condition were selected based on applicant's request.

2. Specific Migration Of Bisphenol A (BPA) Test For Plastic Food Contacting Materials/Articles

With Reference to Commission Regulation (EU) No. 10/2011 and the migration test was conducted once.


I. Test Condition:
60°C for 12 Hours

II. Test Result

<u>Food Simulant</u>	<u>Result (mg/kg)</u>	<u>Limit # (mg/kg)</u>
	<u>Light purple plastic (the biggest)</u>	
50% (v/v) Ethanol	ND	0.6

Remarks: ND = Not Detected
Detection limit = 0.3 mg/kg
Solvents & test condition were selected based on applicant's request.
The result was expressed in mg/kg applying a surface to volume ratio of 6 dm² per kg, which was quoted for samples that are containers or are comparable to containers or which can be filled, with a capacity of less than 500 milliliters or more than 10 liters.
= As per applicant's provided requirement





End of Report

Except where explicitly agreed in writing, all work and services performed by Intertek is subject to our standard Terms and Conditions which can be obtained at our website: <http://www.intertek-twn.com/terms/> . Intertek's responsibility and liability are limited to the terms and conditions of the agreement.

This report is made solely on the basis of your instructions and / or information and materials supplied by you and provide no warranty on the tested sample(s) be truly representative of the sample source. The report is not intended to be a recommendation for any particular course of action, you are responsible for acting as you see fit on the basis of the report results. Intertek is under no obligation to refer to or report upon any facts or circumstances which are outside the specific instructions received and accepts no responsibility to any parties whatsoever, following the issue of the report, for any matters arising outside the agreed scope of the works. This report does not discharge or release you from your legal obligations and duties to any other person. You are the only one authorized to permit copying or distribution of this report (and then only in its entirety). Any such third parties to whom this report may be circulated rely on the content of the report solely at their own risk.

