

Test Report

Applicant: Maymom, LLC
No. 20-7, Aly. 19, Ln. 333,
Zhongzheng Rd., Zhunan Township,
Miaoli County 350, Taiwan (R.O.C.)

Number : TWNC00886518

Issue Date : May 26, 2020

Sample Description:


One (1) Group of Submitted Samples Said To Be :

Item Name : Breast Pump Parts
Item No. : MP012-F24
Manufacturer : Maymom LLC
The batch No. of this product is Batch Jan 2020
Country of Origin : Taiwan
Buyer : Maymom LLC
Date Sample Received : May 18, 2020
Date Test Started : May 18, 2020

Test Conducted:

As requested by the applicant, for details please refer to attached pages.

Authorized By:
On behalf of Intertek Testing Services
Taiwan Limited



Matt Wang
Sr. Manager



Signed by:



Thomas Chou
Manager



Test Conducted :

Test for F.D.A. Regulation on Polypropylene

As per applicant's request with reference to the U.S. 21 CFR Food and Drug Administration part 177.1520 clauses (c)(1.1) and (d) with modification on density and melting point.

Test Sample : Transparent plastic

<u>Test Item</u>	<u>Result</u>	<u>Limit</u>
(A) Density (By Sink-Float Method)	0.889	0.880 – 0.913
(B) Melting Point	153 °C (#)	160 - 180°C (1.1a) /150 - 180 °C (1.1b)
(C) Maximum Extractable Fraction in N-Hexane	2.01 %(W/W)	6.4 %(W/W)
(D) Maximum Soluble Fraction in Xylene	8.16 %(W/W)	9.8 %(W/W)

Remarks: % = Percentage based on the residue by weight
= The limit of clause 1.1a is for polypropylene consists of basic polymers manufactured by the catalytic polymerization of propylene. And the limit of clause 1.1b is for propylene homopolymer consists of basic polymers manufactured by the catalytic polymerization of propylene with a metallocene catalyst.



Sample photo:



End of Report

Except where explicitly agreed in writing, all work and services performed by Intertek is subject to our standard Terms and Conditions which can be obtained at our website: <http://www.intertek-twn.com/terms/>. Intertek's responsibility and liability are limited to the terms and conditions of the agreement.

This report is made solely on the basis of your instructions and / or information and materials supplied by you and provide no warranty on the tested sample(s) be truly representative of the sample source. The report is not intended to be a recommendation for any particular course of action, you are responsible for acting as you see fit on the basis of the report results. Intertek is under no obligation to refer to or report upon any facts or circumstances which are outside the specific instructions received and accepts no responsibility to any parties whatsoever, following the issue of the report, for any matters arising outside the agreed scope of the works. This report does not discharge or release you from your legal obligations and duties to any other person. You are the only one authorized to permit copying or distribution of this report (and then only in its entirety). Any such third parties to whom this report may be circulated rely on the content of the report solely at their own risk

Reporting Statements of Conformity: Please note that the test results contain statement of conformity with the decision rules which are based on the specifications of customers, regulations and standards, and does not consider measurement uncertainty.

